

ProGuard EP Gear Oils Product Data Sheet

ProGuard EP Gear Oils are a series of premium extreme pressure industrial gear lubricants formulated to provide excellent performance protection on enclosed gears of all types. They are blended with selected grades of naturally high viscosity index, thermally stable, paraffinic base stocks and fortified with a carefully selected additive system designed to give high levels of protection against early stages, (micropitting), of gear and bearing wear, rust, oxidation and hydrolytic decomposition meeting or exceeding the following specifications: U.S. Steel 224, AGMA 9005-D94, Cincinnati Milacron, Clean Panel Coker and S-200 Oxidation Tubes.

ProGuard EP Gear Oils are recommended for use in industrial applications where an EP Gear Oils are required. **ProGuard EP Gear Oils** excel in the lubrication of heavily loaded enclosed gear drives and reducers under conditions such as heavily or shock loading occurs. Other **ProGuard EP Gear Oil** applications include the lubrication of chain drives, sprockets, plain and anti-friction bearings and slide guides. **ProGuard** also has been used successfully as mist oil and back-up bearing lubricants.

Benefits

Extreme	pressure	propert	ties to	minimize	wear with	n micro	pitting	protection

☐ Resistance to foaming

□ Oxidation and thermal stability for long life

☐ Excellent rust and corrosion protection

□ Recommended for worm gears and general circulating systems

Typical Characteristics 150 220 460 680 **ProGuard EP Gear Oils** 68 320 2 4 5 6 7 8 AGMA-EP Gravity, API 31.0 29.7 28.4 27.3 26.3 26.0 Weight, lb./gal 7.25 7.31 7.37 7.47 7.81 7.42 Viscosity 66.8 155.4 213.6 325.5 465.8 646.2 40 Deg C, cSt 29.7 39.8 100 Deg C, cSt 8.6 15.3 18.8 24.3 100 DegF,SUS 348 820 1135 1745 2514 3490 210 DegF,SUS 57 82 98 122 148 195 Viscosity Index 90 90 90 90 90 90 5 Pour Point, Deg. F -10 -5 -5 0 10 Timken, OK Load, lbs. 60 60 60 60 65 65 Four Ball EP Test Weld Point, Kg. 250 250 250 250 250 250 47 47 48 49 Load wear index 46 48 12+ 12+ FZG Load Stage 12+ 12+ 12+ 12+ Foam ASTM 892 @0/10 min. Trace/0 Trace/0 Trace/0 Trace/0 Trace/0

090916

Lyden Oil Company

3249 Wales Ave. NW Massillon, OH 44646 (330)832-7800 fax: (330)832-2787 3711 LeHarps Rd. Youngstown, OH (800)362-9410 fax: (330)792-1462 2649 Tracy Rd. Northwood, OH (800)245-9336 fax: (419)666-8790 419 Spring St. Lansing, MI 48101 (800)968-6457 fax: (517)485-0605

24200 W. Outer Dr. Allen Park, MI 48912 (313)383-0097 fax: (313)383-2342